

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Woodland Lifestyle  
3 Wilson Rd  
Motueka 7120  
New Zealand

**Test Number :** 25-001559  
**Issue Date :** 12/06/2025  
**Print Date :** 26/06/2025

**Sample Description** Clients Ref : "Woodland - Pad Attached Laminate"  
Laminate flooring with integrated underlay  
Colour : Timber look  
End Use : Flooring  
Nominal Composition : HDF, laminate + IXPE Underlay  
Nominal Mass per Unit Area/Density : 7318g/m<sup>2</sup>  
Nominal Thickness : 10mm



352380

76749

Page 1 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

  
Chris Campbell  
APPROVED SIGNATORY



  
MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Woodland Lifestyle  
3 Wilson Rd  
Motueka 7120  
New Zealand

**Test Number :** 25-001559  
**Issue Date :** 12/06/2025  
**Print Date :** 26/06/2025

**ISO 9239.1:2010 Part 1      Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source**

Date of Sample Arrival      29-04-2025

Date Tested      12-06-2025

CHF Value	1	2	3	Mean	
Length	9.5	-	-	-	kW/m <sup>2</sup>
Width	6.8	6.8	7.0	6.9	kW/m <sup>2</sup>

HF-30 Value	1	2	3	Mean	
Length	-	-	-	-	kW/m <sup>2</sup>
Width	8.3	8.1	7.9	8.1	kW/m <sup>2</sup>

Smoke Value	1	2	3	Mean	
Length	3	-	-	-	% .min
Width	62	53	23	46	% .min

352380

76749

Page 2 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

  
Chris Campbell  
APPROVED SIGNATORY

  
MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Woodland Lifestyle  
3 Wilson Rd  
Motueka 7120  
New Zealand

**Test Number :** 25-001559  
**Issue Date :** 12/06/2025  
**Print Date :** 26/06/2025

Observation	Yes
Blistering	

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23\pm2^{\circ}\text{C}$  and relative humidity of  $50\pm5\%$  for a minimum of 48 hours prior to testing.

Results in accordance with section 9.4 have not been included in the report. They are available upon request.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

352380

76749

Page 3 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Chris Campbell  
APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR